

Biocompatibility of KYDEX® Thermoplastic Sheet

INTRODUCTION

COMPLIANCE

What is Biocompatibility?

A materials ability to act and perform without impairing basic immunological functions of the body. Biocompatible plastics enhance healing functions without causing injurious, negative physiological, allergic or toxic reactions.

When do products have to be biocompatible?

When in direct contact with human tissue, the material must have the ability to be in contact with a living system without producing an adverse effect. The ISO 10993 series of standards identify three categories of contact (Surface Device, External Communicating Device, Implant Device) and three levels of contact duration (Limited, Prolonged, Permanent).

What is the ISO Standard 10993?

The ISO 10993 set entails a series of standards for evaluating the biocompatibility of medical devices to manage biological risk. The standards are as follows:

- ISO 10993-1 - Evaluation and testing within a risk management process
- ISO 10993-2 - Animal welfare requirements
- ISO 10993-3 - Tests for genotoxicity, carcinogenicity and reproductive toxicity
- ISO 10993-4 - Selection of tests for interactions with blood
- ISO 10993-5 - Tests for in vitro cytotoxicity
- ISO 10993-6 - Tests for local effects after implantation
- ISO 10993-7 - Ethylene oxide sterilization residuals
- ISO 10993-8 - Selection of reference materials
- ISO 10993-9 - Framework for identification and quantification of potential degradation products
- ISO 10993-10 - Tests for irritation and skin sensitization
- ISO 10993-11 - Tests for systemic toxicity
- ISO 10993-12 - Sample preparation and reference materials
- ISO 10993-13 - Identification and quantification of degradation products from polymeric medical devices
- ISO 10993-14 - Identification and quantification of degradation products from ceramics
- ISO 10993-15 - Identification and quantification of degradation products from metals and alloys
- ISO 10993-16 - Toxicokinetic study design for degradation products and leachables
- ISO 10993-17 - Establishment of allowable limits for leachable substances
- ISO 10993-18 - Chemical characterization of medical device materials within a risk management process
- ISO 10993-19 - Physico-chemical, morphological and topographical characterization of materials
- ISO 10993-20 - Principles and methods for immunotoxicology testing of medical devices



Customer Collaboration

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Email: info@kydex.com

appLab™

Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

Biocompatibility of KYDEX® Thermoplastic Sheet

COMPATIBILITY

KYDEX® Thermoplastic products are utilized in Skin Contact applications with Limited to Prolonged Exposure levels. Biocompatible KYDEX® Thermoplastic products have exhibited passing results to both ISO 10993-5: In Vitro Cytotoxicity and ISO 10993-10: Irritation and Skin Sensitization testing. Biocompatible KYDEX® Thermoplastic products are typically utilized in equipment housing, hospital bed, examination table, orthopedic splints and prosthetics, and various other applications.

EXPLANATION OF TESTING

ISO 10993-5: Testing for In Vitro Cytotoxicity – Cytotoxicity testing is a means to determine whether a material contains significant quantities of biologically harmful extractables. Extracts from the test material are exposed to developing cell cultures. The cells are observed for signs of toxicity that include change in size, appearance or the decrease in living cells. The test system is considered suitable if the following conditions are met:

- The viability % for the negative control article should be $\geq 70\%$.
- The viability % for the positive control article should be $< 70\%$.
- The mean of each column of the untreated control must be within $\pm 15\%$ of the untreated control mean.

The lower the viability % value, the higher the cytotoxic potential of the test article is. If viability is reduced to $< 70\%$ of the blank, the test article is considered to have a cytotoxic potential. When tested, most KYDEX® Thermoplastic products resulted in a viability of 95-99%.

ISO 10993-10: Tests for Irritation and Skin Sensitization – ISO 10993-10 is a means to minimize the potential exposure of human patients to irritating materials used in medical devices. Extracts from the test material are applied to the test subject via topical and intradermal application. The injection sites on each test subject are observed for signs of erythema and oedema immediately following injection and at 24 ± 2 hours, 48 ± 2 hours, and 72 ± 2 hours after injection of the test article. Observations of erythema and oedema reactions are scored on a scale of 0-4, then totaled. The primary or cumulative irritation index is characterized by number and description.

0 to 0.4 = Negligible

0.5 to 1.9 = Slight

2.0 to 4.9 = Moderate

5 to 8 = Severe

When tested, KYDEX® Thermoplastic products have exhibited negligible effects.

When tested to ISO 10993-5&10, the following products have shown to have no adverse effects and meet the criteria of being biocompatible materials:

- KYDEX® 100
- KYDEX® 110
- KYDEX® 430
- KYDEX® T
- KYDEX® XD
- KYDEX® XD03

BIOCOMPATIBLE PRODUCTS



Customer Collaboration

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Email: info@kydex.com

appLab™

Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.